

HARDNESS CONVERSION NUMBERS FOR STEEL



2.25	745	---	65.3	---	3.75	262	103.0	26.6	125000
2.30	712	---	---	---	3.80	255	102.0	25.4	121000
2.35	682	---	61.7	---	3.85	248	101.0	24.2	118000
2.40	653	---	60.0	---	3.90	241	100.0	22.8	114000
2.45	627	---	58.7	---	3.95	235	99.0	21.7	111000
2.50	601	---	57.3	---	4.00	229	98.2	20.5	109000
2.55	578	---	56.0	---	4.05	223	97.3	18.8	104000
2.60	555	---	54.7	298000	4.10	217	96.4	17.5	103000
2.65	534	---	53.5	288000	4.15	212	95.5	16	100000
2.70	514	---	52.1	274000	4.20	207	94.6	15.2	99000
2.75	495	---	51.0	264000	4.25	201	93.8	13.8	97000
2.80	477	---	49.6	252000	4.30	197	92.8	12.7	94000
2.85	461	---	48.5	242000	4.35	192	91.9	11.5	92000
2.90	444	---	47.1	230000	4.40	187	90.7	10	90000
2.95	429	---	45.7	219000	4.45	183	90.0	9	89000
3.00	415	---	44.5	212000	4.50	179	89.0	8	88000
3.05	401	---	43.1	202000	4.55	174	87.8	6.4	86000
3.10	388	---	41.8	193000	4.60	170	86.8	5.4	84000
3.15	375	---	40.4	184000	4.65	167	86.0	4.4	83000
3.20	363	---	39.1	177000	4.70	163	85.0	3.3	82000
3.25	352	110.0	37.9	170000	4.80	156	82.9	0.9	80000
3.30	341	109.0	36.6	163000	4.90	149	80.8	---	---
3.35	331	108.5	35.5	158000	5.00	143	78.7	---	---
3.40	321	108.0	34.3	152000	5.10	137	76.4	---	---
3.45	311	107.5	33.1	147000	5.20	131	74.0	---	---
3.50	302	107.0	32.1	143000	5.30	126	72.0	---	---
3.55	293	106.0	30.9	139000	5.40	121	69.8	---	---
3.60	285	105.5	29.9	136000	5.50	116	67.6	---	---
3.65	277	104.5	28.8	131000	5.60	111	65.7	---	---
3.70	269	104.0	27.6	128000					